

# [ hanp HP1320 Evaluation Test Report ]



Item : HP1320

Test date : 2015. 12. 01

Standard (Drum/Toner) : Original/Original

Test pattern : Adobe Reader LSA Mono 5%

Test (Drum/Toner) : hanp HP1320-2 / HP1320 Universal

Test page : 1 ~ 3,000age

Purpose of the test : Toner Matching Test



Model of printer : HP Laser 1320

## ◆ Test Condition

Temp.	Relative Humidity	P.C.R	Developer / R	D / Blade	W / Blade
24±3℃	50±10%			OEM 1 Cycle	



## ◆ Density & Adhesion

page	Original/Original				hanp HP1320-2 / HP1320 Universal			
	Black	Gray	White	Adhesion	Black	Gray	White	Adhesion
Start	1.40	0.42	0.07	99.3%	1.40	0.43	0.05	97.0%
END	1.43	0.46	0.07	100.0%	1.44	0.49	0.04	99.0%



## ◆ Toner Yield & Durability

	Toner Consumption (Average)	G.P.P (Average)	P.P.G (Average)	Transfer rate (Average)	Expected toner yield	Coating thickness		
						Top	Middle	Bottom
						(g)	(g/page)	(page/g)
Original/Original	42.7	0.0427	23.44	93.32		1.2	1.0	1.4
hanp HP1320-2 / HP1320 Universal	44.2	0.0442	22.64	91.33		1.1	0.9	1.2



## ◆ Notice

	Ghost	Back Ground	Filming	Peel Off	Adhesion	Line test
Original/Original	◎	○	◎	◎	◎	○
hanp HP1320-2 / HP1320 Universal	○	◎	◎	◎	◎	○

\*Evaluation  
 ◎ Very good    X Poor  
 ○ Good        XX Bad  
 △ Acceptable

## ◆ Test Result

\_\_\_\_\_

\_\_\_\_\_